

A HIGH DENSITY FIBER OPTIC CABLE

FIELD OF THE INVENTION

The present invention relates generally to fiber optic cables and, more particularly, to high density fiber optic cables.

BACKGROUND OF THE INVENTION

In many applications, it is desirable for a fiber optic cable to include a plurality of optical fibers. With the increased demand for optical communications, there has been a corresponding demand to increase the number of optical fibers, i.e., the fiber count, of a fiber optic cable. By increasing the fiber count of a fiber optic cable, a single fiber optic cable would be able to support additional optical communications channels.

In order to increase the fiber count of fiber optic cables, unitized fiber optic cables have been developed. As shown in Figure 1, a unitized fiber optic cable **10** includes a number of bundles **12** of optical fibers **14** that are stranded about a common central strength member **16**. A unitized fiber optic cable **10** also includes a cable jacket **18** extruded about the bundles **12** of optical fibers **14**, and an optional ripcord **22** for facilitating removal of cable jacket **18**. As shown in Figure 1, each bundle **12** of optical fibers **14** includes at least two and, more commonly, six or twelve optical fibers that are stranded together.

Optical fibers **14** are typically tight buffered optical fibers. A tight buffered optical fiber **14** includes a single mode or multi-mode optical fiber surrounded by an interfacial layer. The interfacial layer can be formed of a Teflon® containing material and is surrounded by a tight buffer layer. The tight buffer layer is typically formed of a plastic, such as polyvinyl chloride (PVC). As an alternative to PVC, the tight buffer layer can be formed of a non-halogenated polyolefin, such as a polyethylene or a polypropylene. Still further, the tight buffer layer can be formed of EVA, nylon or polyester.

Each bundle **12** of optical fibers **14** also generally includes a central strength member **26** about which the plurality of tight buffered optical fibers are stranded. Each bundle **12** of optical fibers **14** further includes a jacket **28** that surrounds the plurality of optical fibers, and an optional ripcord **20** for facilitating removal of jacket **28**. Jacket **28** serves to protect optical fibers **14** and to maintain the bundle of optical fibers in a stranded relationship about central strength member **26**. Jacket **28** is typically formed of a polymer, such as PVC. As an alternative to PVC, jacket **28** may be formed of a fluoro-plastic, such as polyvinylidene fluoride (PVDF), a fluoro-compound as disclosed by U.S. Patent No. 4,963,609 or blends of PVC and PVDF or PVC and polyethylene (PE). Jacket **28** is typically relatively thick and, in one embodiment, has a thickness of about 0.8 millimeters.

During fabrication, a bundle **12** of optical fibers **14** is passed through an extruder cross head and jacket **28** is extruded thereabout in order to maintain the optical fibers in position within the bundle. Since the tight buffer layer of the tight buffered optical fibers **14** is typically formed of a plastic, the plastic that is extruded to form jacket **28** will tend to adhere to the tight buffer layer of the tight buffered optical fibers **14** in the absence of a barrier therebetween. In this regard, the plastic that is extruded to form jacket **28** of a bundle **12** of optical fibers **14** may partially melt the outermost portion of the tight buffer layer of the tight buffered optical fibers **14** such that jacket **28** and the tight buffered optical fibers will adhere to one another as the plastic cools. Unfortunately, the adherence of the tight buffered optical fibers **14** to the surrounding jacket **28** generally decreases the performance of the optical fibers. In this regard, signals propagating along optical fibers **14** generally experience greater attenuation as fiber optic cable **10** is bent or flexed in instances in which the tight buffered optical fibers are adhered to jacket **28** since the optical fibers will no longer be free to move relative to jacket **28** in order to accommodate bending or flexure of fiber optic cable **10**.

Each bundle **12** of optical fibers **14** therefore also generally includes a barrier **30** disposed between the plurality of tight buffered optical fibers and jacket **28** in order to separate the tight buffered optical fibers from jacket **28** and to prevent adherence therebetween that otherwise would result from the extension of jacket **28** about optical fibers **14**. As such, optical fibers **14** can move somewhat relative to jacket **28** as fiber

optic cable 10 is flexed. Barrier 30 is typically formed of a layer of strength members, such as aramid yarn, that are typically stranded about the optical fibers. The layer of strength members is also generally relatively thick and may have a thickness of about 0.2 mm in one embodiment.

Each bundle 12 of optical fibers 14 is typically stranded about common central strength member 16 of fiber optic cable 10. Like central strength member 26 of each bundle 12 of optical fibers 14, central strength member 16 of fiber optic cable 10 is typically formed of a relatively stiff fiber or glass reinforced plastic, or a relatively flexible combination of aramid fibers that may or may not be overcoated with a plastic material. Fiber optic cable 10 also includes a protective cable jacket 18 that surrounds each of the bundles 12 of optical fibers 14. Cable jacket 18 is typically formed of a plastic, such as PVC. As an alternative to PVC, cable jacket 18 may be formed of a fluoro-plastic, such as PVDF, a fluoride-compound or blends of PVC and PVDF or PVC and PE.

As described above in conjunction with jacket 28 that surrounds each bundle 12 of optical fibers 14, cable jacket 18 is also typically extruded over the plurality of bundles of optical fibers. As a result of the plastic materials that form cable jacket 18 and the jackets 28 that surround the respective bundles 12 of optical fibers 14, cable jacket 18 and the jackets that surround the respective bundles of optical fibers may also adhere to one another following the extrusion of cable jacket 18 about the bundles of optical fibers. While the adherence of cable jacket 18 to the jackets 28 of the respective bundles 12 of optical fibers 14 does not impair the performance of fiber optic cable 10 as significantly as adherence between jacket 28 of a bundle 12 of optical fibers 14 and the tight buffer layer of the tight buffered optical fibers, the adherence of cable jacket 18 and the jackets of the respective bundles of optical fibers does disadvantageously impair the flexibility of fiber optic cable 10 somewhat.

Accordingly, fiber optic cable 10 can also include a surface coating on at least that portion of the exterior surface of jacket 28 of each bundle 12 of optical fibers 14 that otherwise would be in contact with cable jacket 18. The surface coating is typically formed of powdered talc that serves to prevent or reduce adhesion between cable jacket 18 and the jackets 28 of the respective bundles 12 of optical fibers 14.

Unitized fiber optic cable **10** as depicted in Figure 1 is generally relatively large. For example, unitized fiber optic cable **10** depicted in Figure 1 having six bundles **12** of optical fibers **14** stranded about a central strength member **16** with each bundle of optical fibers having six tight buffered optical fibers stranded about a respective strength member **26** generally has a diameter of about 18.8 millimeters. In many applications, it is desirable to minimize the size of fiber optic cable **10** while maintaining or increasing the number of optical fibers **14** within fiber optic cable **10**. As such, it would be advantageous to develop a unitized fiber optic cable having a relatively high fiber count while also being somewhat smaller.

SUMMARY OF THE INVENTION

A fiber optic cable is provided according to one aspect of the present invention that includes at least one non-jacketed bundle of optical fibers having a plurality of optical fibers and at least one binder thread encircling the optical fibers to thereby maintain the integrity of the bundle of optical fibers without having to jacket each bundle of optical fibers. The fiber optic cable of this embodiment also includes a cable jacket surrounding the non-jacketed bundle of optical fibers. According to one embodiment, the binder thread is an air entangled, textured, continuous multi-filament thread having no more than 25 twists per inch. In addition, the binder thread may have a TEX number between 18 and 60 and a denier between 150 and 1000, may encircle the optical fibers with a pitch between 10 mm and 70 mm. Further, the binder thread may include a finish, such as a silicone wax emulsion finish, that is inert with respect to those components of the fiber optic cable with which the binder thread comes into contact.

The fiber optic cable according to another aspect of the present invention includes at least one tube assembly having an inner bundle of optical fibers, an outer non-jacketed bundle of optical fibers positioned circumferentially about the inner bundle of optical fibers, and a tubular member, such as a buffer tube, surrounding the outer non-jacketed bundle of optical fibers. Each bundle of optical fibers includes a plurality of optical fibers and at least one binder thread encircling the plurality of optical fibers to maintain the integrity of the respective bundle. Each optical fiber of the inner bundle includes indicia, such as an associated color, for uniquely identifying the respective optical fiber. Similarly, each optical fiber of the outer bundle includes indicia for uniquely identifying

the respective optical fiber. Based upon the indicia of the optical fibers and the bundling of the optical fibers, each optical fiber of a respective tube assembly can therefore be uniquely identified.

A fiber optic cable is provided according to yet another aspect of the present invention that includes a central member, a plurality of non-jacketed bundles of optical fibers extending along the central member with each bundle of optical fibers including a plurality of optical fibers and a binder encircling the optical fibers to maintain the optical fibers in the bundle. The fiber optic cable of this embodiment also includes a cable jacket surrounding the bundles of optical fibers and a separation element for preventing adhesion between the bundles of optical fibers and the cable jacket without jacketing each bundle of optical fibers.

A fiber optic cable according to a further aspect of the present invention includes a plurality of non-jacketed bundles of optical fibers with each bundle including a plurality of optical fibers and a binder thread encircling the optical fibers to maintain the optical fibers in the bundle. The fiber optic cable of this embodiment also includes a separation layer surrounding the bundles of optical fibers and a cable jacket surrounding the separation layer. The separation layer prevents adhesion between the bundles of optical fibers and the cable jacket without having to separately jacket each bundle of optical fibers.

The fiber optic cable of the present invention therefore includes a relatively high count of optical fibers, while reducing the size or diameter of the fiber optic cable. In this regard, the fiber optic cable of the present invention preferably includes a plurality of bundles of optical fibers that are not separately jacketed, thereby permitting the diameter of the fiber optic cable to be reduced. However, the fiber optic cable of the present invention can include a binder, such as a binder thread, for maintaining the integrity of the respective bundles. Moreover, the fiber optic cable can include a separation element for preventing adhesion between the plurality of non-jacketed bundles of optical fibers and the cable jacket such that the optical fibers can move somewhat relative to the cable jacket as the fiber optic cable is bent or flexed such that the optical signals propagating along the optical fibers are not undesirably attenuated as a result of the flexure of the fiber optic cable.

BRIEF DESCRIPTION OF THE DRAWINGS

Having thus described the invention in general terms, reference will now be made to the accompanying drawings, which are not necessarily drawn to scale, and wherein:

Figure 1 is a cross-sectional view of a conventional fiber optic cable having a unitized design;

Figure 2 is a fragmentary perspective view of a fiber optic cable according to one embodiment of the present invention;

Figure 2A is fragmentary perspective view of one bundle of optical fibers of the fiber optic cable of Figure 2 which illustrates the binder thread in more detail;

Figure 3 is a cross-sectional view of the fiber optic cable of Figure 2 taken along line 3-3;

Figure 4 is a fragmentary perspective view of a fiber optic cable according to another embodiment of the present invention;

Figure 5 is a cross-sectional view of the fiber optic cable of Figure 4 taken along line 5-5; and

Figure 6 is a cross-sectional view of a tube assembly of a fiber optic cable according to another embodiment of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

The present invention now will be described more fully hereinafter with reference to the accompanying drawings, in which preferred embodiments of the invention are shown. This invention may, however, be embodied in many different forms and should not be construed as limited to the embodiments set forth herein; rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art. Like numbers refer to like elements throughout.

Referring now to Figure 2, a fiber optic cable **40** according to one embodiment of the present invention is illustrated. Fiber optic cable **40** of the present invention can have other configurations as described below, although the fiber optic cable of Figure 2 will be described in more detail hereinbelow for purposes of illustration. Fiber optic cable **40** includes a plurality of bundles **42** of optical fibers **44**. Typically, fiber optic cable **40** also

Each bundle 42 of optical fibers 44 also includes a binder 48 that encircles the optical fibers to maintain optical fibers 44 in the bundle. In one advantageous embodiment depicted in Figures 2, 2A and 3, a binder thread 48 encircles the optical fibers 44. Fiber optic cable 40 can include various binder threads 48. Binder thread 48 is preferably an air-entangled, textured, continuous multi-filament thread. In addition, binder thread 48 is preferably a synthetic thread that is resistant or impervious to bacterial decomposition which would otherwise create hydrogen which, in turn, may cause undesirable increases in the attenuation of the signals transmitted via optical fibers 44. By way of example, binder thread 48 may be formed of polyester, rayon, nylon or the like. Moreover, binder thread 48 is preferably pre-shrunk.

Binder thread 48 advantageously has a large spread factor and therefore flattens once the binder thread is wrapped about optical fibers 44. Additionally, binder thread 48 preferably readily deforms when subjected to additional forces, such as the forces created by the bend in fiber optic cable 40. Binder thread 48 typically has no more than 25 twists per inch in order to avoid undesirable attenuation of the signals transmitted via optical fibers 44. Most commonly, binder thread 48 has between 2 twists per inch and 6 twists per inch and, more preferably, about 4 twists per inch. Binder thread 48 also preferably has a TEX number between 18 and 60 and, more preferably, between 30 and 40 such as about 35 in one embodiment such that the binder thread has a fluffy feel. Additionally, binder thread 48 advantageously has a denier between about 150 and about 1000 such as about 250 in one embodiment.

Binder thread 48 also preferably includes a finish that is inert with respect to the components of fiber optic cable 40 with which the binder thread will come into contact. In this regard, the finish of binder thread 48 is preferably inert with respect to the tight buffer layer of optical fibers 44, cable jacket 50 and any filling compound such as grease or the like. For example, binder thread 48 of one advantageous embodiment includes a silicone wax emulsion finish that facilitates processing of the binder thread. Binder thread 48 may also be designed to be non-wicking and/or can include a super-absorbent polymer in order to reduce or prevent water migration through fiber optic cable 40. Further, binder thread 48 can include indicia, such as an identification marking or a color, in order to identify the respective bundle of optical fibers encircled by the binder thread

and to distinguish one bundle from another. Alternatively, central member **46** of each bundle **42** of optical fibers **44** can be color coded to uniquely identify the respective bundle.

Binder thread **48** is typically wrapped about a respective bundle **42** of optical fibers **44** in a helical manner with a pitch of between 10 mm and 70 mm and, more preferably, about 50 mm to facilitate fabrication of the bundle of the optical fibers. As illustrated in more detail in Figure 2A, binder thread **48** of one advantageous embodiment includes a pair of threads, namely, a looper thread and a needle thread. As illustrated, one thread, which could be either the looper thread or the needle thread, alternately passes back and forth over the upper portion of bundle **42**, while the other thread alternately passes back and forth under the lower portion of the bundle. With reference to the embodiment of Figure 2A for purposes of example, the leftmost thread at the end of the bundle that is illustrated extends lengthwise along the bundle to a first stitch at which point the threads are secured by means of an overlocked stitch. The thread then helically encircles the lower portion of the bundle to a second overlocked stitch on the far side of the illustrated bundle at which point the threads are again secured to one another. The thread then extends lengthwise along the far side of the bundle to a third overlocked stitch before again helically encircling the lower portion of the bundle to a fourth overlocked stitch. This pattern is repeated for each thread along the length of the bundle in order to secure optical fibers **44** together in an integral manner. In this embodiment, the looper thread and the needle thread are typically secured to one another at a plurality of stitch locations along the length of the bundle of optical fibers, typically at a pitch of 10 mm to 70 mm and, more preferably, at a pitch of 50 mm, by means of an overlocked stitch. The resulting binder thread has a zig-zag appearance and is therefore sometimes termed a zig-zag binder. Binder thread **48** securely maintains the plurality of optical fibers **44** within bundle **42**, while also maintaining the shape and size of the bundle of optical fibers such that the optical fibers need not be disposed within a respective jacket or buffer tube as required by conventional fiber optic cables. By eliminating the jacket or buffer tube in which a bundle of optical fibers were traditionally disposed, the resulting bundle of optical fibers and, in turn, fiber optic cable **40** can be reduced in size relative to a conventional fiber optic cable having the same number of optical fibers.

While a binder thread, such as those described above are advantageous for maintaining optical fibers **44** in a bundle **42**, each bundle of optical fibers can include other types of binders, if so desired. For example, binder **48** may be formed of a film, such as a polymer film, that is wrapped about optical fibers **44** as depicted in Figure 4. In contrast to the polymer jackets that surround the individual bundles of optical fibers of conventional unitized fiber optic cables, the polymer film is generally quite thin, such as between about 1 mil and 10 mils in one embodiment. Additionally, since the polymer film can be wrapped about the bundle **42** of optical fibers **44** and need not be extruded, the polymer film can be wrapped directly about the optical fibers and no barrier is required between the polymer film and the optical fibers since the polymer film will not adhere to the tight buffer layer of the tight buffered optical fibers in the same manner that an extruded polymeric jacket would adhere to the tight buffer layer of the tight buffered optical fibers of a conventional unitized fiber optic cable. Although the polymer film can be formed of various materials, the polymer film of one embodiment is formed of polyester, such as a polyethylene terephthalate, having a thickness of about 1 mil. For example, the polymer film may be a MYLAR[®] film.

Fiber optic cable **40** of the present invention also includes a cable jacket **50** that surrounds each of the bundles **42** of optical fibers **44**, and an optional ripcord **54** for facilitating removal of cable jacket **50**. Cable jacket **50** can be formed of various materials, but is typically formed of a plastic, such as PVC. As an alternative to the PVC, cable jacket **50** may be formed of other plastics including fiber-reinforced polyethylene (FRPE), a fluoro-plastic, such as PVDF, a fluoro-compound as disclosed by U.S. Patent No. 4,963,609 or blends of PVC and PVDF or PVC and PE. As described above in conjunction with the tight buffer layer of the tight buffered optical fibers **44**, cable jacket **50** can also be designed to have increased burn resistance such that the fiber optic cable has a riser, a plenum and/or a low smoke zero halogen rating. In this regard, cable jacket **50** can include aluminum trihydrate, antimony trioxide or other additives that increase the burn resistance of the cable jacket as known to those skilled in the art and as described by U.S. Patent No. 6,167,178. Additionally, cable jacket **50** can be designed to be resistant to UV light, if so desired.

layer **52** of each of these embodiments is generally relatively thin so as not to unnecessarily increase the size of fiber optic cable **40**. For a separation layer **52** formed of a MYLAR[®] film, for example, the mylar film may have a thickness of about 1 mil.

Separation element **52** can be formed in other manners, however, without departing from the spirit and scope of the present invention. For example, in the embodiment of fiber optic cable **40** depicted in Figures 4 and 5, each bundle **42** of optical fibers **44** includes a polymer film **48** surrounding the plurality of tight buffered optical fibers. By appropriately designing polymer film **48**, polymer film **48** not only serves as the binder for the respective bundle **42** of optical fibers **44**, but also serves as the separation element. In this regard, polymer film **48** is preferably formed of a material having a melting point greater than the melting point of the plastic that forms cable jacket **50**. For example, for a fiber optic cable **40** having a cable jacket **50** formed of PVC having a melting point of 190°C, polymer film **48** can be formed of a polyester, such as a MYLAR[®] film, having a melting point of 235°C. As such, the polymer film **48** surrounding each bundle **42** of optical fibers **44** will not melt as cable jacket **50** is extruded about the plurality of bundles of optical fibers. Thus, polymer film **48** will serve to prevent adhesion between cable jacket **50** and the plurality of tight buffered optical fibers **44** of each bundle **42**.

Still further, separation element **52** can be formed of a surface coating on each bundle **42** of optical fibers **44**. In this regard, the surface coating is preferably applied to at least that portion of each bundle **42** of optical fibers **44** that would otherwise contact cable jacket **50**. The surface coating is preferably formed of a material that also has a melting point greater than the melting point of the plastic from which cable jacket **50** is formed. For example, the surface coating may be formed of powdered talc that is applied to the outer surface of the plurality of bundles **42** of optical fibers **44**. The surface coating of talc effectively prevents adhesion between cable jacket **50** and the tight buffered optical fibers **44** as the cable jacket is extruded thereover.

According to the present invention, each individual bundle **42** of optical fibers **44** is unjacketed. That is, each individual bundle **42** of optical fibers **44** is bound together by a binder **48**, such as a binder thread, a thin polymeric layer or the like, and does not include a polymeric jacket as in conventional unitized fiber optic cables. As such, those

embodiments of fiber optic cable **40** in which each bundle **42** is bound with a binder thread **48** permit direct contact between the tight buffered optical fibers of adjacent bundles.

Since each individual bundle **42** of optical fibers **44** does not include a jacket, each individual bundle of optical fibers also need not include a layer of strength members or the like that is otherwise disposed between the jacket and the tight buffered optical fibers in order to prevent adhesion between the jacket and the tight buffered optical fibers of conventional unitized fiber optic cables. As described above, the jackets surrounding the bundles of optical fibers of conventional unitized fiber optic cables are relatively thick. Likewise, the layer of strength members or the like disposed between the jacket of each individual bundle of optical fibers and the tight buffered optical fibers is also relatively thick. By designing fiber optic cable **40** such that the bundles **42** of optical fibers **44** need not include a polymeric jacket or a layer of strength members or the like for separating the tight buffered optical fibers from the polymeric jacket, each bundle of optical fibers can be substantially reduced in size and, correspondingly, fiber optic cable **40** can be substantially reduced in size.

For comparison purposes, fiber optic cable **40** according to one embodiment of the present invention has six bundles **42** of optical fibers **44** with each bundle of optical fibers including six tight buffered optical fibers stranded about a central strength member **46**. While the size and thickness of various cable components may be varied depending upon the application, such as by varying the thickness of cable jacket **50** to alter the crush and impact resistance and/or the flame retardance, fiber optic cable **40** of one embodiment also includes a separation layer **52** of a polyester, such as a MYLAR[®] film surrounding the bundles **42** of optical fibers **44** and a cable jacket **50** having a thickness of 1.3 millimeters surrounding the separation layer such that fiber optic cable **40** has a total diameter of 10.9 millimeters. As described above, a conventional unitized fiber optic cable having the same number of bundles and the same number of total optical fibers generally has a diameter that is substantially larger, such as 18.8 millimeters. As such, the conventional fiber optic cable has a cross-sectional area that is about three times larger than the fiber optic cable according to the foregoing exemplary embodiment. Thus, fiber optic cable **40** of the present invention can include the same number of optical

fibers **44** while being much smaller than conventional fiber optic cables. Alternatively, fiber optic cable **40** can include a greater number of optical fibers, i.e., a higher fiber count, while having the same size as a conventional fiber optic cable.

While various embodiments of fiber optic cable **40** have been described above, fiber optic cable **40** can include other features without departing from the spirit and scope of the present invention. For example, fiber optic cable **40** can be constructed to have increased water resistance by including a variety of water swellable tapes, threads and/or powders. For example, separation layer **52** can be formed of a water swellable tape as described above.

While one unitized design of fiber optic cable **40** has been described hereinabove, fiber optic cable **40** may have other configurations. In this regard, the embodiment of fiber optic cable **40** depicted in Figures 2-5 includes a plurality of individual bundles of optical fibers extending along central member **46** and surrounded by cable jacket **50**. In order to further increase the fiber count of fiber optic cable **40**, however, fiber optic cable **40** can include a number of tube assemblies extending along the central member and surrounded by cable jacket **50** with each tube assembly including multiple bundles of optical fiber. In order to minimize the size of each tube assembly required to contain a predetermined number of optical fibers, however, each bundle of optical fibers of a tube assembly is preferably non-jacketed as described above in conjunction with the embodiment of Figures 2-5.

While the bundles of optical fibers may be arranged in various manners, each tube assembly **54** of fiber optic cable **40** can include concentric bundles **42** of optical fibers **44** with some bundles of optical fibers within other bundles of optical fibers as depicted in the embodiment of Figure 6. In this regard, tube assembly **54** depicted in Figure 6 includes an inner bundle **42a** of optical fibers **44**. Inner bundle **42a** includes a plurality of optical fibers **44** and at least one binder thread **48** encircling the plurality of optical fibers to maintain the integrity of the bundle. Although not illustrated, inner bundle **42a** may also include a central strength member along which optical fibers **44** extend, if so desired. Inner bundle **42a** can include any number of optical fibers **44**, but typically includes 6 or 12 optical fibers. Each optical fiber of inner bundle **42a** preferably includes indicia, such as a color, for uniquely identifying the respective optical fiber relative to other optical

bundle of optical fibers or a surface coating on the outer bundle of optical fibers, as described above.

By encircling inner bundle **42a** with optical fibers **44** of outer bundle **42b**, tube assembly **54** of the embodiment of Figure 6 will include a dense collection of optical fibers in order to maximize the number of optical fibers included within a buffer tube of a particular cross-sectional size. However, each optical fiber of tube assembly **54** can be uniquely identified by means of the indicia, such as the color, of each optical fiber and the separation of the optical fibers into inner and outer bundles.

In order to construct fiber optic cable **40** utilizing tube assembly **54** depicted in Figure 6, a plurality of tube assemblies are extended alongside a central member **46**, typically by being stranded about central member **46**, in the same manner as the individual bundles **42** of optical fibers **44** are extended along central member **46** in the embodiment of Figures 2-5. A cable jacket **50** is then extruded over the plurality of tube assemblies **54**. To prevent adhesion between tubular members **56** of tube assemblies **54** and cable jacket **50**, fiber optic cable **40** can also include a separation element disposed between tube assemblies **54** and cable jacket **50** as described above in conjunction with the other embodiments. By including tube assemblies, each of which generally include multiple bundles of optical fibers, fiber optic cable **40** of this embodiment can include even greater numbers of optical fibers, such as 288 optical fibers or more, while continuing to minimize the overall cross-sectional size of the cable. However, each optical fiber **44** of fiber optic cable **40** of this embodiment may be uniquely identified since tubular member **56** of each tube assembly **54** may include indicia, such as a color, to uniquely identify the respective tube assembly and the indicia, such as the color, of each optical fiber and the separation of the optical fibers into inner and outer bundles permit each optical fiber of a respective tube assembly to be uniquely identified as described above.

Many modifications and other embodiments of the invention will come to mind to one skilled in the art to which this invention pertains having the benefit of the teachings presented in the foregoing descriptions and the associated drawings. Therefore, it is to be understood that the invention is not to be limited to the specific embodiments disclosed and that modifications and other embodiments are intended to be included within the

